Attorney Docket Q64166

AMENDMENT UNDER 37 C.F.R. § 1.114(c)

U.S. Application No.: 09/840,917

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the

application:

**LISTING OF CLAIMS:** 

1-4. (canceled).

5. (currently amended): A method for producing an inorganic oxide powder which

comprises a step-steps of continuously introducing, into a dry-way pulverizer, an inorganic oxide

in an amount of 100 parts by volume and air, nitrogen or a gas mixture thereof in an amount of

from about 25,000 to about 160,000 parts by volume to pulverize the inorganic oxide in the dry-

way pulverizer, and discharging the pulverized inorganic oxide.

6. (original): A method for producing an inorganic oxide powder according to claim

5, wherein the dry-way pulverizer is a dry-way pulverizer having a system for introducing a gas

to a pulverization chamber of the pulverizer through a pipeline from an air supply apparatus.

7. (previously presented): A method for producing an inorganic oxide powder

according to claim 5 or claim 6, wherein the dry-way pulverizer is a mill selected from the group

consisting of a rotation ball mill, a vibration ball mill, a planetary ball mill and a stirring mill.

8. (previously presented): A method for producing an inorganic oxide powder

according to claim 5 or claim 6, wherein the dry-way pulverizer is a medium-stirring pulverizer.

2

Attorney Docket Q64166

AMENDMENT UNDER 37 C.F.R. § 1.114(c) U.S. Application No.: 09/840,917

- 9. (previously presented): A method for producing an alumina powder which comprises a step of pulverizing an aluminum oxide with purity of about 99.9% or higher and a BET specific surface area of from about 1 to about 70 m²/g in a medium-stirring pulverizer under dry conditions at a specific energy consumption of from about 0.3 to about 1 kWh/kg.
- 10. (previously presented): A method for producing an alumina powder according to claim 9, wherein the aluminum oxide is an aluminum oxide obtained by an alkoxide method comprising a step of hydrolyzing an organoaluminium compound.